

6/28/2011

Attn: Brundy Pursley  
Piazza Stoneworks, LLC  
3817 Martinez Blvd. Suite A  
Augusta, GA 30907

Ref: Peel Adhesion Testing w/ Pecora 890FTS-TXTR

Tracking #663P13

Mr. Pursley:

Upon your request, the Technical Service Group has evaluated the peel adhesion properties of Pecora 890FTS-TXTR (Textured) Silicone Sealant on the substrates provided. This testing was performed in accordance with ASTM C794. The following results were obtained:

**Peel Adhesion Testing (ASTM C794)<sup>1</sup>**

<b>Substrates:</b>	Precast Veneer A Precast Veneer B Precast Veneer C Precast Veneer D
<b>Sealant:</b>	Pecora 890FTS-TXTR
<b>Primer:</b>	None required
<b>Surface Preparation:</b>	Coarse natural bristle brush
<b>Results:</b>	<b>Pass</b>

<sup>1</sup> ASTM C794 Pass Criteria: >5.0 lbf, <25% adhesive failure

Should you have any questions concerning the test methods employed or the results reported here please do not hesitate to call the Technical Service Dept.

Sincerely,



Michael D. Murphy  
Sr. Technical Service Representative



Roy D. Cannon, Jr.  
Director of Technical Service

Pc: Marshall Murphey, Nexgen

